

Property	Test Method	Value
Density (g/cm ³)	D792A or D1505	0.941 - 0.955
Melt Index (g/10 min)	D1238	0.39 max.
Flexural Modulus (psi)	D790	80,000 min.
Tensile Strength @ Yield (psi)	D638	3,000 min.
ESCR, Condition B (10%, 50°C)	D1693	F10 > 96 hours
Hydrostatic Design Basis (psi)	D2387	NPR

* NPR - Not Pressure Rated